

**PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE**  
**REMODEX**  
**ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO**  
Spółka z o.o.

Gruszczyn, ul. Leśna 12  
62-006 Kobylnica

e-mail: [biuro@remodex.com.pl](mailto:biuro@remodex.com.pl)  
KRS 0000099068

tel./fax. 61 817-49-97  
tel. kom. 601 391 825

SIGN: BW/JK/52/18

DATE: 2018-02-28

Order from: 2017-12-28

## TEST REPORT

### Determination of the abrasion resistance of fabric by Martindale method

- |  |  |
|--|--|
| <b>1. Name and type of article -</b>                             | <b>Fabric TW-S2</b>  |
| <b>2. CLIENT -</b>   | P.H. „STEMA” Stefan Boczyło<br>ul. Bystrzycka 17<br>58-100 ŚWIDNICA    |
| <b>3. Type of test</b>   |  |
| - <b>resistance to abrasion by Martindale method</b>             | - inspection intervals after 1000, 2000, 5000 and 10000 cycles         |
| - loading – nominal pressure 12 kPa                              | - the number cycles: average – <b>50.000</b>                           |
| - translational movement along Lissajous tracks                  | - after 60000 cycles partial wipe of fibers.                           |
| - <b>resistance to pilling</b><br>(modified Martindale’s method) | - after 2000 cycles – degree of change <b>5</b><br><b>(no changes)</b> |
| - loading – 260 g,   | - after 5000 cycles – degree of change <b>5</b><br><b>(no changes)</b> |
| - translational movement along Lissajous tracks                  |  |
| <b>4. Documents identifying article -</b>                        | order.   |

This article was tested in accordance with the test procedures described in:

**PN-EN ISO 12947-2:2000**  
**PN-EN ISO 12945-2:2002**  
for conformity with PN-EN 14465:2005, annex A


#### TEST RESULTS:

#### POSITIVE

**Article fulfill the requirements PN-EN 14465:2005, annex A. at the level category A**

**Attention:** The test sample was acclimated according to PN-EN 20139:1993 (ISO 139)

Test operator

  
.....  
/M Sc. (Eng.) Jacek Konieczny

FREZES ZARZĄDU

  
mgr inż. Piotr Błaszczak

TEST REPORT contain 1 pages

The test results are only valid for the article tested. This TEST REPORT shall not be reproduced except in full, without the written approval of the laboratory.

**PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE  
REMODEX**

**ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO**  
Spółka z o.o.

Gruszczyn, ul. Leśna 12  
62-006 Kobylnica

e-mail: [biuro@remodex.com.pl](mailto:biuro@remodex.com.pl)  
KRS 0000099068

tel./fax. 61 817-49-97  
tel. kom. 601 391 825

SIGN: BW/JK/50/18

DATE: 2018-02-28

Order from: 2017-12-28

**TEST REPORT**

**Determination of the abrasion resistance of fabric by Martindale method**

1. *Name and type of article -* **Fabric TW-N1**
2. *CLIENT -* P.H. „STEMA” Stefan Boczyło  
ul. Bystrzycka 17  
58-100 ŚWIDNICA
3. *Type of test*
- **resistance to abrasion by Martindale method**
    - inspection intervals after 1000, 2000, 5000 and 10000 cycles
    - loading – nominal pressure 12 kPa
    - translational movement along Lissajous tracks
    - the number cycles: average – **100.000**
    - **no destruction point is obtained in all four samples; no damage of fabric.**
  - **resistance to pilling**  
(modified Martindale’s method)
    - loading – 260 g,
    - translational movement along Lissajous tracks
    - after 2000 cycles – degree of change **5 (no changes)**
    - after 5000 cycles – degree of change **5 (no changes)**
4. *Documents identifying article -* order.

This article was tested in accordance with the test procedures described in:


**PN-EN ISO 12947-2:2000**  
**PN-EN ISO 12945-2:2002**  
for conformity with PN-EN 14465:2005, annex A

**TEST RESULTS:**

**POSITIVE**  
**Article fulfill the requirements PN-EN 14465:2005, annex A. at the level category A**

**Attention:** The test sample was acclimated according to PN-EN 20139:1993 (ISO 139)

Test operator

  
/M Sc. (Eng.) Jacek Konieczny

PREZES ZARZĄDU

  
mgr inż. Piotr Błaszczak

TEST REPORT contain 1 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced except in full, without the written approval of the laboratory.