

PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE
REMODEX

ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO

Spółka z o.o.

Gruszczyn, ul. Leśna 12
62-006 Kobylnica

e-mail: biuro@remodex.com.pl
KRS 0000099068

tel./fax 061 817-49-97
tel. kom. 601 391 825

SIGN: BW/JK/51/18

DATE: 2018-02-28

Order from: 2017-12-28

TEST REPORT No: 9/18/P
Assessment of ignitability

1. *Sample* - Fabric TW-S2 – filling – standard polyurethane foam T-30.

2. *CLIENT* –

P.H. „STEMA” Stefan Boczyło
ul. Bystrzycka 17
58-100 ŚWIDNICA

3. *Documents identifying article* –

order + described sample.

4. *This article was tested in accordance with the test procedures described in:*

PN-EN 1021-1:2014


5. *Ignition source:*

smouldering cigarette

6. *TEST RESULTS:*

POSITIVE

Test operator


.....
/M Sc. (Eng.) Jacek Koniczny

PREZES ZARZĄDU


mgr inż. Piotr Błaszczyk

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

Test report – Assessment of ignitability

Materials tested - Fabric TW-S2 – filling – standard polyurethane foam T-30.

1. Ignition source: smouldering cigarette

2. Test sample conditions:

- temperature - 21 °C
- relative humidity - 55 %
- time - 24 h

3. Test results – NON-IGNITION

Criteria		smouldering cigarette		Comments																		
		1	2																			
Smouldering criteria	Unsafe escalating combustion	NO	NO	Test 1 – smouldering time of the cigarette 18 min. 23 s After this time, the cigarette went out, smoking ceased; the cigarette burned out to 5/6 length (it did not burn out completely). Test 2 – smouldering time of the cigarette 23 min. 47 s The cigarette burned out the whole length.																		
	Test assembly consumed	NO	NO																			
	Smoulders to extremities	NO	NO																			
	Smoulders through thickness	NO	NO																			
	Smoulders more than 1 hour	NO	NO		Dimensions of extent of the damage (mm)																	
	In final examination occurrence of smoulder	NO	NO																			
Flaming criteria	Occurrence of flames	NO	NO	<table border="1"> <thead> <tr> <th colspan="3">horizontal assembly</th> <th colspan="3">vertical assembly</th> </tr> <tr> <th>len- gth</th> <th>wi- dth</th> <th>de- pth</th> <th>len- gth</th> <th>wi- dth</th> <th>de- pth</th> </tr> </thead> <tbody> <tr> <td>64</td> <td>16</td> <td>11</td> <td>65</td> <td>21</td> <td>8</td> </tr> </tbody> </table>	horizontal assembly			vertical assembly			len- gth	wi- dth	de- pth	len- gth	wi- dth	de- pth	64	16	11	65	21	8
				horizontal assembly			vertical assembly															
				len- gth	wi- dth	de- pth	len- gth	wi- dth	de- pth													
64	16	11	65	21	8																	

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

SIGNED:  LABORATORIUM

PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE
REMODEX

ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO

Spółka z o.o.

Gruszczyn, ul. Leśna 12
62-006 Kobylnica

e-mail: biuro@remodex.com.pl
KRS 0000099068

tel./fax 061 817-49-97
tel. kom. 601 391 825

SIGN: BW/JK/49/18

DATE: 2018-02-28

Order from: 2017-12-28

TEST REPORT No: 8/18/P

Assessment of ignitability

1. *Sample* - Fabric TW-N1 – filling – standard polyurethane foam T-30.

2. *CLIENT* –

P.H. „STEMA” Stefan Boczyło
ul. Bystrzycka 17
58-100 ŚWIDNICA

3. *Documents identifying article* –

order + described sample.

4. *This article was tested in accordance with the test procedures described in:*

PN-EN 1021-1:2014


5. *Ignition source:*

smouldering cigarette

6. *TEST RESULTS:*

POSITIVE

Test operator


.....
/M Sc. (Eng.) Jacek Końieczny

FREZES ZARZĄDU


mgr inż. Piotr Błaszczek

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

TEST REPORT No: 8/18/P

Test report – Assessment of ignitability

Materials tested - Fabric TW-N1 – filling – standard polyurethane foam T-30.

1. Ignition source: smouldering cigarette

2. Test sample conditions:

- temperature - 21 °C
- relative humidity - 55 %
- time - 24 h

3. Test results – NON-IGNITION

Criteria		smouldering cigarette		Comments	
		1	2		
Smouldering criteria	Unsafe escalating combustion	NO	NO	Test 1 – smouldering time of the cigarette 8 min. 14 s Test 2 – smouldering time of the cigarette 7 min. 15 s After these times, cigarettes went out. In both trials, the cigarettes burned out by 1/6 of their length.	
	Test assembly consumed	NO	NO		
	Smoulders to extremities	NO	NO		
	Smoulders through thickness	NO	NO		
	Smoulders more than 1 hour	NO	NO		Dimensions of extent of the damage (mm)
	In final examination occurrence of smoulder	NO	NO		
Flaming criteria	Occurrence of flames	NO	NO	horizontal assembly	
				vertical assembly	
				len-gth wi-dth de-pth len-gth wi-dth de-pth	
				18 14 3 18 13 2	

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

SIGNED:

 LABORATORIUM