

**PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE
REMODEX**

**ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO
Spółka z o.o.**

Gruszczyń, ul. Leśna 12
62-006 Kobylnica

e-mail: biuro@remodex.com.pl
KRS 0000099068

tel./fax 061 817-49-97
tel. kom. 601 391 825

SIGN: BW/JK/55/18

DATE: 2018-02-28

Order from: 2017-12-28

TEST REPORT No: 11/18/P
Assessment of ignitability

1. Sample - Fabric TW-S1 – filling – standard polyurethane foam T-30.

2. CLIENT –

P.H. „STEMA” Stefan Boczyło
ul. Bystrzycka 17
58-100 ŚWIDNICA

3. Documents identifying article –

order + described sample.

**4. This article was tested in accordance
with the test procedures described in:**

PN-EN 1021-1:2014

5. Ignition source:

smouldering cigarette

6. TEST RESULTS:

POSITIVE

Test operator

/M Sc. (Eng.) Jacek Konieczny

FREZES ZARZĄDU

mgr inż. Piotr Błaszczyk

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

Test report – Assessment of ignitability

Materials tested - Fabric TW-S1 – filling – standard polyurethane foam T-30.

1. Ignition source: smouldering cigarette

2. Test sample conditions:

- temperature - 21 °C
- relative humidity - 55 %
- time - 24 h

3. Test results – NON-IGNITION

Criteria	smouldering cigarette		Comments					
	1	2						
Smouldering criteria	Unsafe escalating combustion	NO	NO					
	Test assembly consumed	NO	NO					
	Smoulders to extremities	NO	NO					
	Smoulders through thickness	NO	NO					
	Smoulders more than 1 hour	NO	NO					
	In final examination occurrence of smoulder	NO	NO					
Flaming criteria	Occurrence of flames	NO	Dimensions of extent of the damage (mm)					
		horizontal assembly	vertical assembly					
		length	width	depth	length	width	depth	
		69	15	8	68	23	7	

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

SIGNED: .. 
LABORATORIUM

**PRZEDSIĘBIORSTWO USŁUGOWO REMONTOWE
REMODEX**

**ZAKŁAD BADAŃ I WDROŻEŃ PRZEMYSŁU MEBLARSKIEGO
Spółka z o.o.**

Gruszczyń, ul. Leśna 12
62-006 Kobylnica

e-mail: biuro@remodex.com.pl
KRS 0000099068

tel./fax 061 817-49-97
tel. kom. 601 391 825

SIGN: BW/JK/49/18

DATE: 2018-02-28

Order from: 2017-12-28

TEST REPORT No: 8/18/P
Assessment of ignitability

1. Sample - Fabric TW-N1 – filling – standard polyurethane foam T-30.

2. CLIENT –

P.H. „STEMA” Stefan Boczyło
ul. Bystrzycka 17
58-100 ŚWIDNICA

3. Documents identifying article –

order + described sample.

**4. This article was tested in accordance
with the test procedures described in:**

PN-EN 1021-1:2014

5. Ignition source:

smouldering cigarette

6. TEST RESULTS:

POSITIVE

Test operator


.....
/M Sc.(Eng.) Jacek Konieczny

PREZES ZARZĄDU

mgr inż. Piotr Bielecki

TEST REPORT contain 2 pages

The test results are only valid for the article tested.

This TEST REPORT shall not be reproduced, except in full, without the written approval of the laboratory.

Test report – Assessment of ignitability

Materials tested - Fabric TW-N1 – filling – standard polyurethane foam T-30.

1. Ignition source: smouldering cigarette

2. Test sample conditions:

- temperature - 21 °C
- relative humidity - 55 %
- time - 24 h

3. Test results – NON-IGNITION

Criteria		smouldering cigarette		Comments	
		1	2		
Smouldering criteria	Unsafe escalating combustion	NO	NO	Test 1 – smouldering time of the cigarette 8 min. 14 s Test 2 – smouldering time of the cigarette 7 min. 15 s After these times, cigarettes went out. In both trials, the cigarettes burned out by 1/6 of their length.	
	Test assembly consumed	NO	NO		
	Smoulders to extremities	NO	NO		
	Smoulders through thickness	NO	NO		
	Smoulders more than 1 hour	NO	NO	Dimensions of extent of the damage (mm)	
	In final examination occurrence of smoulder	NO	NO		
Flaming criteria	Occurrence of flames	NO	NO	horizontal assembly	vertical assembly
				length 18	width 14

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

SIGNED:
Mow
LABORATORIUM